

**ABRASION RESISTANCE  
OF  
LITHURIN I & IIS**



**ABRASION RESISTANCE  
OF  
LITHURIN I & IIS**

**Report for ab lindec**

**Ref: ABL/ABR/051009B**

**M.SADEGZADEH BSc MBA PhD CEng MICE**

**ASTON SERVICES**

**October 2009**

# CONTENTS

	Page No.
Contents	2
List of Tables	3
1.0 Introduction	4
2.0 Abrasion Resistance of Concrete	4
3.0 Abrasion Test Results and Discussion	5
4.0 Conclusions	6
5.0 References	9

## LIST OF TABLES

Table	Title	Page No.
1	Classification of Concrete Floor Slabs in Medium Industrial Environment	7
2	Classification of Abrasion Resistance According to BS 8204: Part 2	7
3	Classification of Abrasion Resistance BCA Abrasion Tester to EN13892-4	8
4	Summary of Abrasion Test Results	8

## 1.0 INTRODUCTION

This report has been prepared in response to a request made by ab lindec, to Carry out investigation of the abrasion resistance of Lithurin I & IIS applied to concrete. Six samples were submitted for testing: Three with Lithurin I & IIS and three control with no surface treatment.

## 2.0 ABRASION RESISTANCE OF CONCRETE

Extensive experimental work, undertaken both in Europe (1) (2) and North America (3) (4) (5), has demonstrated that the abrasion resistance of concrete is influenced by many factors. The main influence, however, may be summarised as follows:-

- (i) Compressive Strength
- (ii) Physical Properties of the Aggregate
- (iii) Construction Procedures and Finishing Technique
- (iv) Curing
- (v) Subsequent Surface Treatment

The role of these has been thoroughly discussed elsewhere (1) (2), and so a similar discussion is not included in this report. Throughout this report the abrasion resistance is expressed in terms of the depth of wear produced when the surface is exposed to abrasion by Standard Rolling Wheels (6). This system, originally developed by the Cement & Concrete Association has become a widely accepted measure of abrasion resistance. Indeed, a classification has been suggested that limits values of wear depth (7,8). This original classification has been extended and now been included in the latest edition of BS 8204: part 2:2003(9). The depth of wear is determined at the

completion of 2850 revs which is approximates to 15 minutes. The original classification is given in Table 1 and the more detailed classification of abrasion resistance and limiting depths of wear for the accelerated abrasion test is provided in Table 2, clearly, the greater the depth of wear, the lower the abrasion resistance.

Table 3 shows classification according to EN 13813:2002 (E). Reference should also be made to BS EN 13813:2002(E) Paragraph 5.2.3 Wear Resistance Table 5 (reference (10)), also EN 13892-4.

The accelerated abrasion tests were performed in accordance with the requirements of BS 8204: part 2:2003(9) and EN 13892-4.

### 3.0 ABRASION TEST RESULTS AND DISCUSSION

One accelerated abrasion test was performed on each sample slabs. The abrasion test results are summarised in Table 4. The depths of wear obtained for Lithurin I & IIS samples range between 0.02 mm to 0.04 mm, with a mean depth of wear of 0.03 mm. Whereas, for the control samples without any surface treatment the depth of wear obtained range between 0.21 mm and 0.24 mm, with a mean depth of wear of 0.22 mm. When these mean depths of wear are compared with the BS 8204; Part 2:2003: classification of abrasion resistance and proposed limiting depths of wear for the accelerated abrasion test, Table 2, it can be seen that Lithurin I & IIS can be classified as "Special/DF" and control samples as "AR4/DF".

The results clearly demonstrates that application of Lithurin I & IIS to concrete surface significantly increases the abrasion resistance.

#### 4.0 CONCLUSIONS

Based on the results arising from this work, the following conclusions can be presented:-

(i)The abrasion resistance quality of Lithurin I & IIS applied to concrete can be classified as "Special/DF" in accordance with BS 8204: Part 2:2003.

(ii)The abrasion resistance quality of concrete surface is significantly increased by application of Lithurin I & IIS.



**M.Sadegzadeh BSc MBA PhD CEng MICE**

Quality of Concrete Slab	Abrasion Depth (mm)
GOOD	< 0.2
NORMAL	0.2 – 0.4
POOR	> 0.40

Table 1: Classification of Concrete Floor Slabs in Medium Industrial Environmental

BS 8204 Class	Duty	Type of Concrete	Concrete grade N/mm <sup>2</sup>	Minimum cement content kg/m <sup>3</sup>	Maximum wear depth mm
AR0.5 Special/DF	Very heavy duty	Specially designed	Special mixes and dry-shake or sprinkle finishes, resins etc		0.05
AR1/DF	Heavy duty	Specially designed			0.1
AR2/DF	Medium duty	Direct finish concrete	C40/50	400	0.2
AR4/DF	Light duty	Direct finish concrete	C32/40	325	0.4

Table 2: Classification of abrasion resistance according to BS 8204: Part 2:2003 (based on reference 9)



Class	AR6	AR4	AR2	AR1	AR0,5
Maximum wear depth in $\mu\text{m}$	600	400	200	100	50

Table 3: Classification according to EN 13813:2002  
The wear resistance BCA is designated by an "AR" (for Abrasion Resistance) followed by the maximum depth of wear in  $100\mu\text{m}$ .

Specimen I.D	Test No.	Depth of Wear (mm)	Mean Depth of Wear (mm)	Classification according to BS EN 8204:Pt 2: 2003
Lithurin I&IIS	1	0.02	0.03	Special/DF
	2	0.04		
	3	0.03		
Control	1	0.22	0.22	AR2/DF
	2	0.24		
	3	0.21		

Table 4: Summary of Abrasion Test Results

## 5.0 REFERENCES

1. Sadegzadeh, M. "Abrasion Resistance of Concrete", PhD Thesis, Aston University, 1985.
2. Cement and Concrete Association Report for the year 1979.
3. Smith, F.L. "The Effect of Aggregate Quality on the Resistance of Concrete to Abrasion", Cement and Concrete, STP No.205, ASTM, 1958, pp 91-106.
4. Prior, M.E."Abrasion Resistance", Significance of Tests and Properties of Concrete and Concrete Making Materials", ASTM STP No. 169-A, 1966, pp 246-260.
5. Fentress, B. "Slab Construction Practices Compared with Wear Tests", J.Am.Con.Inst. July 11973, pp 486-491.
6. Kettle, R.J. and Sadegzadeh, M. "Abrasion Resistance", Concrete Testing for Durability, Concrete Society, London, 1984, pp.65-72.
7. Kettle, R.J. and Sadegzadeh M, "Recent Research Developments on Abrasion Resistance", Concrete, Nov. 1986, pp. 29-31.
8. Kettle, R.J. and Sadegzadeh M, "Field Investigation of Abrasion Resistance", Materials and Structures, Vol.20, No.116, March 1987.
9. BS 8204: Part 2: 2003. Screeds bases and in-situ floorings- Part 2 concrete. Concrete wearing surfaces- Code of Practice. BSI London 2003.
- 10 BS EN 13813:2002 Screed material and floor screeds – Screed material – Properties and requirements

