

Instructions for Lithurin® Seal

1. Apply with a low-pressure sprayer or a can with spray-nozzle
2. Work the material into the surface with a soft brush to ensure good absorption. Keep the surface damp (at a temp. of +10-13 °C) for approx. 15-20 minutes.
3. If the surface starts to dry, wet it with more Lithurin® Seal. Ensure that no part of the surface dries during the absorption period. The material becomes sticky if it takes too long, particularly with higher temperatures.
4. Remove excess material with the brush, while the material is still fluid. (Apply with pressure on the brush to remove excess material).
5. Be sure to remove all excess material that the floor doesn't absorb.
6. The simplest method is to use steps 1 to 6, in stages of 100 m² per person. (2 persons = 200 m²)
7. To ensure that the concrete surface receives the right amount of material, the instructions above must be followed.
8. Under certain conditions, e.g. low temperature, strong wind etc., the absorption time is longer and at higher temperatures the absorption time is shorter.

Consumption:

- Machine trowelled surface: approx. 0.15 litres/m²
- Non-machine trowelled surface: approx. 0.2-0.4 litres/m²



ab lindec® endeavours to provide correct information about technical properties and handling of its products. However, while ab lindec® has no control over the way in which the products are mixed and laid, or the conditions under which they set, ab lindec® can in no way be held responsible. ab lindec® is only responsible for the quality of the products at the time of delivery.